



Helmitin[®] 14030

- Type of Adhesive** This is a non-flammable, two-component polychloroprene adhesive.
- Product Benefits** It ensures excellent quality of adhesion under extreme application conditions while at the same time offering short drying times. Following curing of the adhesive film, parts bonded using this adhesive display outstanding resistance to heat, cold and moisture, as well as to the effects of grease and plasticisers. These values are dependent on the composition of the rubber compound and the load exerted upon it.
- Typical Applications** For the adhesion and repair of conveyor belts, as well as for lining steel cylinders and drums with rubber materials.
- Suitable substrates** Conveyor belts.

Typical Properties

Property	Value
Base	polychloroprene
Colour	black
Viscosity	Brookfield (at 20°C) approx. 3,700 mPas*
Density	approx. 1.45 g/cm ³
Storage life	12 months



Application Instructions

Application: brush, trowel or blade.

- addition of hardeners:
 - 5% Swift® Hardener 9502 (flame-retardant)
 - 5% Swift® Hardener 9503 (highly flammable)
- pot life: approx. 3 hours
- airing time: 10 - 15 minutes
- contact adhesion time: approx. 30 minutes
- curing time: approx. 24 hours
- consumption: approx. 300 to 400 g/m²
- sensitive to frost: yes – reversible
- EU hazard identification: irritant – see safety data sheet

Prior to processing, the adhesive should be carefully mixed with the curing agent. The elements to be bonded must be clean and free of all grease and dust particles. We strongly recommend using our Swift® Clean 9041 to carry out degreasing in advance. Rubber elements must be abraded, dusted and glued immediately in order to avoid any risk of oxidation on the newly-abraded rubber surfaces. For the bonding of metals, we recommend the use of a primer.

For application conditions, please refer to the technical data sheet.

- The best adhesion to different rubber materials is achieved within 15-30 minutes following the addition of the curing agent.

Following extended storage of the mixture, adhesion is noticeably reduced. A brush or a trowel is used to apply the adhesive/curing agent mixture to the materials that have been prepared for adhesion. When adhering rubber to rubber, it is advisable to apply a second layer of adhesive following an airing time of at least 10 minutes. When gluing textiles, three layers of adhesive should be applied in order to achieve full-surface adhesion. As before, the minimum drying time before application of the next layer of adhesive is 10 minutes.

Adhesion is carried out by bringing together both glued surfaces and hitting them firmly with a hammer. If it is possible to use a press, this would be the preferred method.

- In order to avoid failed adhesions, the temperature of both the room and the adhesive should not be below 18°C.



Cleaning Instructions	Please contact your local Sales Office for available cleaning solutions.
Typical Packaging	Please contact your local Sales Office for available packaging options.
Storage Conditions	In the sealed original packaging and protected from sunlight, dust, moisture and high temperatures. Clean and dry at a temperature of between +10°C and +30°C.
Disposal Advice	Please refer to the MSDS for disposal instructions.
Safety Advice	Please refer to the MSDS for safety advice.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.



H.B. Fuller

H.B. Fuller Company

info-europe@hbfuller.com
www.hbfuller.com/
eimea/contact-us